



Eurofins Product Testing A/S Smedeskovvej 38 8464 Galten Denmark

VOC@eurofins.com www.eurofins.com/VOC-testing

Essve Produkter AB P.O Box 7091 Esbogatan 14 SE-164 74 Kista SWEDEN

# VOC TEST REPORT

# **M1**

25 January 2017

#### **Sample Information** 1

Sample name	Akryl Flex 25% Brun	
Batch no.	29.04.15	
Production date	-	
Product type	Joint sealant	
Sample reception	15/12/2016	

The tested sample Akryl Flex 25% brun has been selected as being representative for the sealant of the type. This type includes the products Akryl Flex 25 % Vit, Akryl Flex 25 % Listvit, Akryl Flex 25 % Ljusgrå, Akryl Flex 25 % Grå, Akryl Flex 25 % Mörkgrå, Akryl Flex 25 % Antracit, Akryl Flex 25 % Beige, Akryl Flex 25 % Brun, Akryl Flex 25 % Svart which according to the information of the manufacturer are based on the same recipe. The tested product Akryl Flex 25 % Brun is considered as the "worst-case"-product.

#### 2 Brief Evaluation of the Results

Regulation or protocol	Conclusion	Version of regulation or protocol
M1	Pass	M1 Protocol of January 2015

Full details based on the testing and direct comparison with limit values is available in the following pages

Maria Pelle Chemist

Janne R. Norup

Chemist





# **Table of contents**

1		Sample Information	1
2		Brief Evaluation of the Results	1
3		Applied Test Methods	3
	3.1	General Test References	3
	3.2	Specific Laboratory Sampling and Analyses	3
4		Test Parameters, Sample Preparation and Deviations	4
	4.1	VOC Emission Chamber Test Parameters	4
	4.2	Preparation of the Test Specimen	4
	4.3	Picture of Sample	4
	4.4	Deviations from Referenced Protocols and Regulations	4
5		Results	5
	5.1	VOC Emission Test Results after 28 Days	5
	5.2	Sensory Testing	6
6		Summary and Evaluation of the Results	7
	6.1	Comparison with M1 Limit Values	7
7		Appendices	8
	7.1	Chromatogram of VOC Emissions after 28 Days	8
	7.2	How to Understand the Results	9
	7.3	Description of VOC Emission Test	10
	7.4	Quality Assurance	12
	7.5	Accreditation	12
	7.6	Uncertainty of the Test Method	12







# **3 Applied Test Methods**

## 3.1 General Test References

Regulation, protocol or standard	Version	Reporting limit VOC [µg/m³]	Calculation of TVOC	Combined uncertainty <sup>*</sup> [RSD(%)]
CEN/TS 16516	October 2013	5	Toluene equivalents	22%
ISO 16000 -3 -6 -9 -11	2006-2011 depending on part	2	Toluene equivalents	22%
ASTM D5116	2010	-	-	-
M1	M1 Protocol of January 2015	5	Toluene equivalents	22%
EN 15251 <sup>,</sup> appendix C*	2007	2	Toluene equivalents	22%

## 3.2 Specific Laboratory Sampling and Analyses

Procedure	External Method	Internal SOP	Quantification limit / sampling volume	Analytical principle	Uncertainty <sup>*</sup> [RSD(%)]
Sample preparation	ISO 16000-11:2006, EN16402:2013, CDPH, AgBB/DIBt, EMICODE	71M549810	-	-	-
VOC emission chamber testing	ISO 16000-9:2006, CEN/TS 16516:2013	71M549811	-	Chamber and air control	-
Sampling of VOC	ISO 16000-6:2011, CEN/TS 16516:2013	71M549812	5 L	Tenax TA	-
Analysis of VOC	ISO 16000-6:2011, CEN/TS 16516:2013	71M542808B	1 µg/m³	ATD-GC/MS	10%
Sampling of aldehydes	ISO 16000-3:2011, CEN/TS 16516:2013	71M549812	35 L	DNPH	-
Analysis of aldehydes	ISO 16000-3:2011, EN 717-1, CEN/TS 16516:2013	71M548400	3-6 µg/m³	HPLC-UV	10%
Sampling of Ammonia	NIOSH 6015:1994	71M549812	100 L	H <sub>2</sub> SO <sub>4</sub> coated Silicagel	-
Analysis of Ammonia	NIOSH 6015:1994	71M544430	10 µg/m³	Spectrofotometry	10%
Odour/sensory testing*	ISO 16000-28:2012	71M549822	-	Odour panel	10%





# 4 Test Parameters, Sample Preparation and Deviations


#### 4.1 VOC Emission Chamber Test Parameters

Parameter	Value	Parameter	Value
Chamber volume, V[L]	119	Preconditioning period	-
Air Change rate, n[h <sup>-1</sup> ]	0.5	Test period	22/12/2016 - 19/01/2017
Relative humidity of supply air, RH [%]	50 ± 3	Area specific ventilation rate, q [m/h or m <sup>3</sup> /m <sup>2</sup> /h]	71
Temperature of supply air, T [°C]	23 ± 1	Loading factor [m²/m³]	0.007
		Test scenario	Very small area

## 4.2 Preparation of the Test Specimen

The sample was applied onto a glass plate and drawn off over a model giving a 3 mm thick and uniform layer with a broadness of 10 mm.

## 4.3 Picture of Sample



## 4.4 Deviations from Referenced Protocols and Regulations

No deviations from the referenced test methods were observed.





# **5** Results

## 5.1 VOC Emission Test Results after 28 Days

	CAS No.	Retention time	ID- Cat	Concentration	SER
		[min]		[µg/m³]	[µg/(m²*h)]
VOC compounds					
Ethylene glycol *	107-21-1	2.90	2	6.4	450
TVOC				6.4	450
VVOC compounds None determined					
TVVOC				< 5	< 400
SVOC compounds					
None determined					
TSVOC				< 5	< 400
Carcinogens					
Total carcinogens				< 1	< 80
Add. compounds					
Formaldehyde	50-00-0		1	< 3	< 300
Ammonia	7664-41-7		1	< 10	< 800





# 5.2 Sensory Testing

	Acceptance		Acceptance
First Assessment			
Participant 1	0.2	Participant 10	0.9
Participant 2	0.3	Participant 11	1.0
Participant 3	0.4	Participant 12	1.0
Participant 4	0.2	Participant 13	0.9
Participant 5	-0.1	Participant 14	-0.2
Participant 6	0.7	Participant 15	0.7
Participant 7	0.9	Participant 16	0.8
Participant 8	0.4	Participant 17	0.5
Participant 9	0.9	Participant 18	0.6
Second Assessment			
Participant 1	0.2	Participant 10	0.9
Participant 2	0.4	Participant 11	1.0
Participant 3	0.5	Participant 12	1.0
Participant 4	0.2	Participant 13	0.9
Participant 5	-0.1	Participant 14	-0.3
Participant 6	0.7	Participant 15	0.7
Participant 7	0.9	Participant 16	0.8
Participant 8	0.5	Participant 17	0.5
Participant 9	0.9	Participant 18	0.8
Final Results			
Average assessment	0.6		
90% confidence interval	0.5-0.7	-	
Standard deviation	0.4		





# 6 Summary and Evaluation of the Results

## 6.1 Comparison with M1 Limit Values


Parameter	Concentration mg/m³	Limit Value mg/m³
TVOC	0.0064	≤ 0.02
Formaldehyde	< 0.003	≤ 0.01
Ammonia	< 0.01	≤ 0.01
Total carcinogens	< 0.001	≤ 0.001
Odour (dimensionless)	0.6	≥ 0.0





# 7 Appendices

## 7.1 Chromatogram of VOC Emissions after 28 Days







## 7.2 How to Understand the Results

### 7.2.1 Acronyms Used in the Report

- < Means less than
- > Means bigger than
- \* Not a part of our accreditation
- ¤ Please see section regarding uncertainty in the Appendices.
- § Deviation from method. Please see deviation section
- a The method is not optimal for very volatile compounds. For these substances smaller results and a higher measurement uncertainty cannot be ruled out.
- b The component originates from the wooden panels and is thus removed.
- c The results have been corrected by the emission from wooden panels.
- d Very polar organic compounds are not suitable for reliable quantification using tenax TA adsorbent and HP-5 GC column. A high degree of uncertainty must be expected.

SER Specific emission rate.

#### 7.2.2 Explanation of ID Category

#### Categories of Identity:

1: Identified and specifically calibrated

2: Identified by comparison with a mass spectrum obtained from library and supported by other information. Calibrated as toluene equivalent.

3: Identified by comparison with a mass spectrum obtained from a library. Calibrated as toluene equivalent.

4: Not identified, calibrated as toluene equivalent.





### 7.3 Description of VOC Emission Test

#### 7.3.1 Test Chamber

The test chamber is made of stainless steel. A multi-step air clean-up is performed before loading the chamber, and a blank check of the empty chamber is performed.

The chamber operation parameters are as described in the test method section. (CEN/TS 16516, ISO 16000-9, internal method no.: 71M549811).

#### 7.3.2 Expression of the Test Results

All test results are calculated as specific emission rate, and as extrapolated air concentration in the European Reference Room (CEN/TS 16516, AgBB, EMICODE, M1 and Indoor Air Comfort).

#### 7.3.3 Testing of Carcinogenic VOCs

The emission of carcinogens (EU Categories C1A and C1B, as per European law) is tested by drawing sample air from the test chamber outlet through Tenax TA tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by ATD-GC/MS (automated thermal desorption coupled with gas chromatography and mass spectroscopy using 30 m HP-5 (slightly polar) column with 0.25 mm ID and 0.25  $\mu$ m film, Agilent) (CEN/TS 16516, ISO 16000-6, internal methods no.: 71M549812 / 71M542808B).

All identified carcinogenic VOCs are listed; if a carcinogenic VOC is not listed then it has not been detected. Quantification is performed using the TIC signal and authentic response factors, or the relative response factors relative to toluene for the individual compounds.

This test only covers substances that can be adsorbed on Tenax TA and can be thermally desorbed. If other emissions occur, then these substances cannot be detected (or with limited reliability only).

#### 7.3.4 Testing of VOC, SVOC and VVOC

The emissions of volatile organic compounds are tested by drawing sample air from the test chamber outlet through Tenax TA tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by ATD-GC/MS using HP-5 column (30 m, 0.25mm ID, 0.25µm film) (CEN/TS 16516, ISO 16000-6, internal methods no.: 71M549812 / 71M542808B).

All single substances that are listed with a LCI/NIK value in the latest publications (hereafter referred to as target compounds) are identified if present. All other appearing VOCs are identified as far as possible. Quantification of target compounds is done using the TIC signal and authentic response factors, or the relative response factors relative to toluene. For certain compound groups, which differ significantly in chemistry from toluene, quantification is performed relative to a representative member of the group for more accurate and precise results. This can include quantification of for example glycols and acids. In addition to that, all results are also expressed in toluene equivalents. All non-target compounds, as well as all non-identified substances, are quantified in toluene equivalents.

The results of the individual substances are calculated in three groups depending on their retention time when analyzing using a non-polar column (HP-1):

- Volatile Organic Compounds (VOC) are defined as: All substances eluting between and including
- n-hexane (n-C6) and n-hexadecane (n-C16)
- Semi-Volatile Organic Compounds (SVOC) are defined as: All substances eluting after
- n-hexadecane (n-C16) and before and including n-docosane (n-C22)
- Very Volatile Organic Compounds (VVOC) are defined as: All substances eluting before n-hexane (n-C6).





Total Volatile Organic Compounds (TVOC) is calculated by summation of all individual VOCs with a concentration  $\ge 5 \ \mu g/m^3$ . The TVOC can be expressed either in toluene equivalents as defined in CEN/TS 16516 and similar to ISO 16000-6, or as the sum of concentrations using specific or relative response factors. In the case of summation of concentrations using authentic or relative response factors, the toluene equivalent is applied to all non-target and non-identified VOCs before summing up. Compounds regarded as VOC in line with the above definition but elute before n-C6 or after n-C16 on the HP-5 column are treated as VOC, and are thus added to the TVOC.

Total Semi-Volatile Organic Compounds (TSVOC) is calculated by the summation of all individual SVOCs expressed in toluene equivalents with a concentration  $\geq 5 \ \mu g/m^3$ , as defined in CEN/TS 16516. VOCs that are regarded as VOC in line with the above definition, but elute after n-C16 in this test, are not added to the TSVOC.

Total Very Volatile Organic Compounds (TVVOC) is calculated by the summation of all individual VVOCs with a concentration  $\ge 5 \ \mu g/m^3$  and expressed in toluene equivalents. VOCs that are regarded as VOC in line with the above definition, but elute before n-C6 in this test, are not added to the TVVOC.

This test only covers substances which can be adsorbed on Tenax TA and can be thermally desorbed. If emissions of substances outside these specifications occur then these substances cannot be detected (or with limited reliability only).

#### 7.3.5 Testing of Aldehydes

The presence of aldehydes is tested by drawing air samples from the test chamber outlet through DNPHcoated silicagel tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by solvent desorption and subsequently by HPLC and UV-/diode array detection.

The absence of formaldehyde and other aldehydes is stated if UV detector response at the specific wavelength is lacking at the specific retention time in the chromatogram. Otherwise it is checked whether the reporting limit is exceeded. In this case the identity is finally checked by comparing full scan sample UV spectra with full scan standard UV spectra.

#### 7.3.6 Testing of Ammonia

The presence of ammonia was tested by drawing air samples from the chamber outlet through silicagel tubes coated with sulphuric acid after 28 days. Analysis was done by solvent desorption and UV/VIS spectroscopy (internal methods: 71M549812 / 71M544430).

The absence of ammonia was stated if the signal was lacking at the specific wavelength. Otherwise it was checked whether the detection limit was exceeded.


#### 7.3.7 Sensory Testing

The sensory testing was done after 28 days storage under controlled conditions in the testing chamber. The test panel assessed the odour first of the room air and then give the odour rating twice for each chamber. Between two assessments there was a minimum break of 2 minutes. Each single judgement was based on the odour impression after 2-3 inhalations. The odour was rated immediately after each assessment on a continuous scale with values between +1 (clearly acceptable) and -1 (clearly unacceptable), with just acceptable = +0.1 and just unacceptable = -0.1. The scale was read with an accuracy of  $\pm$  0.1. The result was calculated as the average of the assessments from the odour rating of the panel, and only results with a note > 0.1 are accepted. Only panel members rating clean moistened air as acceptable (> 0.8) were considered in the calculation.

Sensory Acceptance:







## 7.4 Quality Assurance

Before loading the test chamber, a blank check of the empty chamber is performed and compliance with background concentrations in accordance with CEN/TS 16516 / ISO 16000-9 is determined.

Air sampling at the chamber outlet and subsequent analysis is performed in duplicate. Relative humidity, temperature and air change rate in the chambers is logged every 5 minutes and checked daily. A double determination is performed on random samples at a regular interval and results are registered in a control chart to ensure the uncertainty and reproducibility of the method.

The stability of the analytical system is checked by a general function test of device and column, and by use of control charts for monitoring the response of individual substances prior to each analytical sequence.

### 7.5 Accreditation

The testing methods described above are accredited on line with EN ISO/IEC 17025 by DANAK (no. 522). This accreditation is valid worldwide due to mutual approvals of the national accreditation bodies (ILAC/IAF, see also www.eurofins.com/galten.aspx#accreditation.

Not all parameters are covered by this accreditation. The accreditation does not cover parameters marked with an asterisk (\*), however analysis of these parameters is conducted at the same level of quality as for the accredited parameters.

### 7.6 Uncertainty of the Test Method

The relative standard deviation of the overall analysis is 22%. The expanded uncertainty Um equals 2 x RSD. For further information please visit www.eurofins.dk/uncertainty.