


DURASTEEL®



Composite insulation board

DURASTEEL® consists of a calcium silicate core reinforced on both sides with perforated galvanised steel covering sheets.

The punched lugs in the steel sheets are pressed into the core board giving the DURASTEEL® composite board a very high mechanical strength once the drying process is finished.

DURASTEEL® comes in two thicknesses and the material is classified as class A1, non-combustible.

Technical data			
Thickness	mm	6	9.5
Building material class	DIN 4102	A1, non-combustible	A1, non-combustible
Classification temperature			
Permanent stress	°C	400	400
Short term up to	°C	1000	1000
Bulk density	kg/m³	2800	2210
Cold compressive strength	N/mm²	60	60
Bending strength	N/mm²	109	84
Tensile strength	N/mm²	32	30
Modulus of elasticity E	N/mm²	55000	40000
Thermal conductivity			
20 °C	W/m K	0.55	0.55
Sound insulation	dB	28	30
Board weight	kg/m²	16.8	21
Moisture content (air-dry)	%	6	6
Water absorption	%	14	14

Delivery sizes			
Thickness	mm	6	9.5
Length	mm	2500	2500
Width	mm	1200	1200
Other sizes are available on request.			

Production tolerances			
Thickness	mm	+ 1.5 / - 0	± 1.0
Length and width	mm	± 2.0	± 2.0





DURASTEEL®

Properties & advantages

- High mechanical strength
- Impact and shock proof
- Resistant to water and frost, suited for outdoor use
- Good chemical resistance
- Large-size and thin boards
- Load-bearing
- Non-combustible
- Non-scratch surface

Application areas

HEAVY INDUSTRY

- DURASTEEL® boards are mainly used in the steel and non-ferrous industry as:
 - Heat shield against cyclic or permanent heat radiation
 - Heat shield against metal splashes or sparks
 - Mobile heat shields
 - Office walls close to heat sources
- Flue gas ducts
- Inner wall lining of fire stations

OIL AND GAS


- Heat shields
- Blast and fire walls
- Heavy duty enclosures



Working & processing

To cut and shape DURASTEEL® we recommend the use of a guillotine shear or a water jet. On site it is best to use a compass saw with a fine-toothed blade. Attachment holes should be made using a metal drill on a milling head.

When cutting to size, the maximum workplace concentration values for inhalable dust must be observed. Dust extraction is recommended. See product safety information sheet.



All data contained in this publication are provided in good faith and are correct at the time of printing. Data are representative of production and are subject to normal production fluctuations, they should not be deemed to constitute or imply any warranty of performance, the user is held responsible for determining the suitability of the products for the given application. Errors and omissions excepted. All drawings and representations remain our exclusive property and cannot be used, totally or in part, without our prior written approval. Excepts, reproductions, copies, etc. of our publications require our prior approval. This publication renders all previous ones invalid. Our terms of delivery and payment apply in the event of any claim. Promat and Microtherm are registered trademarks. © Copyright Etex NV, Brussels, Belgium. All rights reserved. 2017-09

